



CLIENT: TOP FLIGHT SUPPLIES
7839 S. Peoria St.
Eaglewood CO 80112
United States

Attn: Scott Huppert

Test Report No: 4377738PP01R1

Date: 20 September 2019

This report supersedes previous report dated on 26 October 2018 for error on company name

SAMPLE(S) SUBMITTED

BY THE CLIENT AS: Ceramic Coating Protection, Color: Clear.

DATE OF RECEIPT: 11 October 2018

TESTING PERIOD: 19 – 26 October 2018

TEST REQUESTED: The submitted samples were tested for Pencil Hardness as per ASTM D 3363, Alkali & Acid test as per 5% (Sodium Carbonate & Hydrochloric Acid) Solution, and Salt Spray test as per 3% Sodium Chloride Solution.

TEST RESULTS: See pages 2 to 3

PREPARED BY:

**Hayford Mensah, Report Writer
Packaging & Materials Lab**

**SIGNED FOR AND ON BEHALF OF
SGS NORTH AMERICA INC.,**

**Frank Savino, Lab Manager
Packaging & Materials Lab**

Page 1 of 3

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/terms-and-conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

CLIENT: TOP FLIGHT SUPPLIES

RESULTS:

Test: **Pencil Hardness Testing**
 ASTM D 3363

Material: Ceramic Coating Protection, Color: Clear.		
Sample	Scratch Hardness	Gouge Hardness
1	2B	HB

Note: 2B was the highest pencil that will not rupture or scratch sample.
 HB was the highest pencil that will leave sample uncut.

Scale of hardness testing.

6B – 5B – 4B – 3B – 2B – B – HB – F – H – 2H – 3H – 4H – 5H – 6H

Softer Harder


Material: Ceramic Coating Protection, Color: Clear.			
Test Performed	Solution Used	Time/ Duration	Results/ Observation
Alkali	5% Sodium Carbonate (Na ₂ CO ₃)	24hrs	No observable corrosion to ceramic coated metal but minor tarnishing to non-coated metallic side of panel
Acid	5% Hydrochloric Acid (HCl)	24hrs	No observable corrosion to ceramic coated metal but major wearing to non-coated metallic side of panel
Salt	3% Sodium Chloride (NaCl)	96hrs	No observable corrosion to ceramic coated metal but minor corrosion to non-coated metallic side of panel

Note: Two samples for each test condition were submerged in solution for specified time, then inspected for abnormalities.

CLIENT: TOP FLIGHT SUPPLIES

RESULTS:

Sample Photos



End of Report

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/terms-and-conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.